

 Polymers - A Property Database**Table: Polysulfones - Upper Use Temperature (long)****Table Type: Interactive Table****Total Number of Rows: 1**

[< First Page] [Previous Page] [Jump To Page] [Next Page] [Last Page] [1 of 1]

Select Rows **Find Data in Table** **Filter Data in Table** **Sort Table** **Show / Hide Columns**  **Back To Table of Contents**  **Help**

<input type="checkbox"/>	no.	material or substance name	max continuous service temp (°C)	note	reference
	A-Z				
<input checked="" type="checkbox"/>	1	<u>Polysulfone</u>	160	UL 746 [1]	[1] Encycl. Polym. Sci. Eng., Vol. 13, 2nd edn., (ed. J.I. Kroschwitz), John Wiley and Sons, 1985.

Polymers - A Property Database
Copyright © 2000 by Chapman & Hall/CRC Press

 **Polymers - A Property Database**
Table: Polyolefins - Upper Us Temperature (long)
[First Page](#) [Previous Page](#) [Jump To Page](#) [Next Page](#) [Last Page](#)

1 of 1

Table Type: Interactive Table**Total Number of Rows: 2**
[Select Rows](#) [Find Data in Table](#) [Filter Data in Table](#) [A-Z Sort](#) [Show / Hide Columns](#) [Back To Table of Contents](#) [Help](#)

<input type="checkbox"/>	no.	material or substance name	max continuous service temp (°C)	note	reference
	A-Z				
<input type="checkbox"/>	1	Polypropylene	85	approx.	
<input type="checkbox"/>	2	Polypropylene	120	approx. [23]	[23] Engineered Materials Handbook, (ASM International Handbook Committee), ASM International, 1995.

 Polymers - A Property Database
 Copyright © 2000 by Chapman & Hall/CRC Press